

Fibreboards — Specifications —

Part 1: General requirements

The European Standard EN 622-1:2003 has the status of a
British Standard

ICS 79.060.20

National foreword

This British Standard is the official English language version of EN 622-1:2003. It supersedes BS EN 622-1:1997 which is withdrawn.

The UK participation in its preparation was entrusted to Technical Committee B/541, Wood based panels, which has the responsibility to:

- aid enquirers to understand the text;
- present to the responsible international/European committee any enquiries on the interpretation, or proposals for change, and keep the UK interests informed;
- monitor related international and European developments and promulgate them in the UK.

A list of organizations represented on this committee can be obtained on request to its secretary.

Cross-references

The British Standards which implement international or European publications referred to in this document may be found in the *BSI Catalogue* under the section entitled "International Standards Correspondence Index", or by using the "Search" facility of the *BSI Electronic Catalogue* or of British Standards Online.

This publication does not purport to include all the necessary provisions of a contract. Users are responsible for its correct application.

Compliance with a British Standard does not of itself confer immunity from legal obligations.

This British Standard, was published under the authority of the Standards Policy and Strategy Committee on 4 July 2003

Summary of pages

This document comprises a front cover, an inside front cover, the EN title page, pages 2 to 9 and a back cover.

The BSI copyright date displayed in this document indicates when the document was last issued.

Amendments issued since publication

Amd. No.	Date	Comments

© BSI 4 July 2003

English version

Fibreboards - Specifications - Part 1: General requirements

Panneaux de fibres - Exigences - Partie 1: Exigences
générales

Faserplatten - Anforderungen - Teil 1: Allgemeine
Anforderungen

This European Standard was approved by CEN on 3 March 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Requirements	4
4 Verification of compliance	6
4.1 General.....	6
4.2 External control.....	6
4.3 Factory production control.....	6
5 Marking	7
Annex A (normative) Voluntary colour coding system for fibreboards	8
Bibliography	9

Foreword

This document (EN 622-1:2003) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2003, and conflicting national standards shall be withdrawn at the latest by October 2003.

This document supersedes EN 622-1:1997.

This standard is one of a series specifying requirements for fibreboards. The titles of the other parts of this series are listed in clause 2.

Compared to EN 622-1:1997 the following modifications have been made:

- a) annex A with A-deviations for formaldehyde emission has been deleted. The formaldehyde classes according to EN 13986 have taken into account in Table 1 and Table 3.
- b) EN 326-2 and EN 326-3 have been added as normative references in clause 4.

Annex A is normative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

1 Scope

This European Standard specifies the requirements for some properties which are common to all uncoated fibre-board types as defined in EN 316.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 120, *Wood-based panels — Determination of formaldehyde content — Extraction method called the perforator method.*

EN 316, *Wood fibreboards — Definition, classification and symbols.*

EN 322, *Wood-based panels — Determination of moisture content.*

EN 323, *Wood-based panels — Determination of density.*

EN 324-1, *Wood-based panels — Determination of dimensions of boards — Part 1: Determination of thickness width and length.*

EN 324-2, *Wood-based panels — Determination of dimensions of boards — Part 2: Determination of squareness and edge straightness.*

EN 326-2, *Wood-based panels — Sampling, cutting and inspection — Part 2: Quality control in the factory.*

EN 326-3, *Wood-based panels — Sampling, cutting and inspection — Part 3: Inspection of a consignment of panels.*

EN 622-2, *Fibreboards — Specifications — Part 2: Requirements for hardboards.*

EN 622-3, *Fibreboards — Specifications — Part 3: Requirements for medium boards.*

EN 622-4, *Fibreboards — Specifications — Part 4: Requirements for softboards.*

EN 622-5, *Fibreboards — Specifications — Part 5: Requirements for dry process boards (MDF).*

ENV 717-1, *Wood-based panels — Determination of formaldehyde release — Part 1: Formaldehyde emission by the chamber method.*

EN 717-2, *Wood-based panels — Determination of formaldehyde release — Part 2: Formaldehyde release by the gas analysis method.*

3 Requirements

Fibreboards shall comply with the general requirements listed in Table 1 and the thickness tolerances listed in Table 2 when dispatched from the producing factory. For certain uses of fibreboards (see specific standards for fibreboards types and general performance standards for wood-based panels), in the case of dispatch in cut sizes, or when further machined (e.g. tongued and grooved), special tolerances for nominal dimensions, squareness and edge straightness may be agreed upon. The values given in Table 1 and Table 2 for tolerances for nominal dimensions (thickness, width and length), squareness, edge straightness and density within a panel, are characterized by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of 65 %. Properties not required for specific board types are marked “—”.

The requirements relating to formaldehyde potential (perforator value) shall be met by the 95 percentile value based on test values of individual boards. The 95 percentile value shall be equal to or less than the value given in Table 1.

Table 1 — General requirements for different types of fibreboard at dispatch

Property	Test method	Board Type			
		Hard-boards (HB)	Medium boards (MBL and MBH)	Soft-boards (SB)	Dry process boards (MDF)
Tolerances on nominal dimensions:					
Thickness	EN 324-1	see Table 2 ± 2 mm/m, maximum ± 5 mm			
Length and width	EN 324-1				
Squareness tolerances	EN 324-2	2 mm/m			
Edge straightness tolerance	EN 324-2	1,5 mm/m			
Moisture content	EN 322	4 % to 9 %	4 % to 9 %	4 % to 9 %	4 % to 11 %
Tolerance on mean density within a panel	EN 323	—	—	—	± 7 %
Formaldehyde potential	EN 120 or ENV 717-1				
Class E1					
Perforator value ^a	EN 120 or ENV 717-1	—	—	—	≤ 8 mg/100 g oven dry board Release ≤ 0,124 mg/m ³ air
Steady state emission value ^b	EN 120 or ENV 717-1	—	—	—	
Class E2					
Perforator value ^a	EN 120 or ENV 717-1	—	—	—	≤ 30 mg/100 g oven dry board Release > 0,124 mg/m ³ air
Steady state emission value ^b	EN 120 or ENV 717-1	—	—	—	
<p>^a The perforator values apply to panels with a moisture content H of 6,5 %. In the case of dry process boards with different moisture contents, the perforator value shall be multiplied by a factor F calculated from the following equations:</p> <p>For panels with moisture contents in the range of $4 \% \leq H \leq 9 \%$:</p> $F = -0,133 H + 1,86$ <p>Respectively for panels with moisture contents $H < 4 \%$ and $H > 9 \%$:</p> $F = 0,636 + 3,12 e^{(-0,346 H)}$ <p>^b Required for initial type testing other than for established products where initial type testing may also be done on the basis of existing data with EN 120 or EN 717-2 testing, either from factory production control or from external inspection.</p>					

Table 2 — Tolerances on nominal thickness for fibreboards at dispatch

Board types	Hardboards (HB)	Nominal thickness (mm)		
		≤ 3,5	> 3,5 to 5,5	> 5,5
		± 0,3 mm	± 0,5 mm	± 0,7 mm
	Medium boards (MBL and MBH)	Nominal thickness (mm)		
		≤ 10	> 10	
		± 0,7 mm	± 0,8 mm	
	Softboards (SB)	Nominal thickness (mm)		
		≤ 10	> 10 to 19	> 19
		± 0,7 mm	± 1,2 mm	± 1,8 mm
	Dry process boards (MDF)	Nominal thickness (mm)		
		≤ 6	> 6 bis 19	> 19
		± 0,2 mm	± 0,2 mm	± 0,3 mm

4 Verification of compliance

4.1 General

Verification of compliance with this European Standard shall be carried out using the test methods listed in Table 1.

4.2 External control

External control of the factory, if any, shall be carried out according to EN 326-2.

The inspection of a consignment of panels shall be carried out according to EN 326-3.

In the case of formaldehyde potential determined by EN 120 perforator method, however, for both external control and inspection of a consignment of panels, the respective requirements set out in Table 1 shall be the arithmetic mean value of at least three boards. Additionally, no individual board shall exceed an upper tolerance limit of + 10 %.

4.3 Factory production control

Factory production control shall be carried out according to EN 326-2.

The properties listed in Tables 1 and 2 shall be controlled, using intervals between tests not exceeding those given in Table 3. Sampling shall be carried out at random. Alternative test methods and/or unconditioned test pieces may be used if a valid correlation to the specified test methods can be proven. The intervals between tests given in Table 3 are related to a production under statistical control.

Table 3 — Maximum intervals between tests for each production line

Property	Maximum test interval
Formaldehyde potential ^a	
Class E1	24 h per type of board
Class E2	1 week per type of board
Moisture content	8 h per type of board
All other properties listed in Tables 1 and 2	8 h per type and thickness range
^a Some types of fibreboards are known to release little or no formaldehyde. In these cases, maximum test intervals may be increased. However, it remains the responsibility of the producer or inspection agency, if any, to ensure compliance with this European Standard.	

5 Marking

Marking of fibreboards shall be carried out in accordance with EN 622-2, EN 622-3, EN 622-4 and EN 622-5 as appropriate.

Colour coding is voluntary. If applied, it shall comply with the system shown in annex A. This standard does not exclude colour dyeing of the whole board or individual layers of the board according to traditional national practices.

Annex A
(normative)

Voluntary colour coding system for fibreboards

Two colours are used in each case. The first colour defines the panel as either intended for general purposes use or for load-bearing applications (either one or two stripes of this colour are used). The second colour identifies the panel as being suitable for use either in dry or in humid or in exterior conditions.

The colours used are as follows:

First colour	white	general purpose
First colour	yellow	load-bearing
Second colour	blue	dry conditions
Second colour	green	humid conditions
Second colour	brown	exterior conditions.

Bibliography

EN 13986, *Wood-based panels for use in construction — Characteristics, evaluation of conformity and marking.*

BSI — British Standards Institution

BSI is the independent national body responsible for preparing British Standards. It presents the UK view on standards in Europe and at the international level. It is incorporated by Royal Charter.

Revisions

British Standards are updated by amendment or revision. Users of British Standards should make sure that they possess the latest amendments or editions.

It is the constant aim of BSI to improve the quality of our products and services. We would be grateful if anyone finding an inaccuracy or ambiguity while using this British Standard would inform the Secretary of the technical committee responsible, the identity of which can be found on the inside front cover. Tel: +44 (0)20 8996 9000. Fax: +44 (0)20 8996 7400.

BSI offers members an individual updating service called PLUS which ensures that subscribers automatically receive the latest editions of standards.

Buying standards

Orders for all BSI, international and foreign standards publications should be addressed to Customer Services. Tel: +44 (0)20 8996 9001. Fax: +44 (0)20 8996 7001. Email: orders@bsi-global.com. Standards are also available from the BSI website at <http://www.bsi-global.com>.

In response to orders for international standards, it is BSI policy to supply the BSI implementation of those that have been published as British Standards, unless otherwise requested.

Information on standards

BSI provides a wide range of information on national, European and international standards through its Library and its Technical Help to Exporters Service. Various BSI electronic information services are also available which give details on all its products and services. Contact the Information Centre. Tel: +44 (0)20 8996 7111. Fax: +44 (0)20 8996 7048. Email: info@bsi-global.com.

Subscribing members of BSI are kept up to date with standards developments and receive substantial discounts on the purchase price of standards. For details of these and other benefits contact Membership Administration. Tel: +44 (0)20 8996 7002. Fax: +44 (0)20 8996 7001. Email: membership@bsi-global.com.

Information regarding online access to British Standards via British Standards Online can be found at <http://www.bsi-global.com/bsonline>.

Further information about BSI is available on the BSI website at <http://www.bsi-global.com>.

Copyright

Copyright subsists in all BSI publications. BSI also holds the copyright, in the UK, of the publications of the international standardization bodies. Except as permitted under the Copyright, Designs and Patents Act 1988 no extract may be reproduced, stored in a retrieval system or transmitted in any form or by any means – electronic, photocopying, recording or otherwise – without prior written permission from BSI.

This does not preclude the free use, in the course of implementing the standard, of necessary details such as symbols, and size, type or grade designations. If these details are to be used for any other purpose than implementation then the prior written permission of BSI must be obtained.

Details and advice can be obtained from the Copyright & Licensing Manager. Tel: +44 (0)20 8996 7070. Fax: +44 (0)20 8996 7553. Email: copyright@bsi-global.com.